



DECLARATION OF PERFORMANCE

DoP-1948-SQ-EUCA-05-01-CE2+

Manufacturer Identification

Manufacturer	Representative in the EU	Manufacturing Facility
Uruply S.A. Ruta 5, Km 400,5 Tacuarembó, 45000 – Uruguay Tel.: +598 (0)63 222 00	Lumin Forest Products Ltd Carmanhall Road, SANDYFORD Dublin 18 – D18 Y3X2 – Ireland europe-sales@lumin.com	Uruply S.A. Ruta 5, Km 400,5 Tacuarembó, 45000 – Uruguay

Product Identification

Product Type	Technical Class	Intended Use	AVCP (*)
Lumin® Plywood <i>Eucalyptus Plywood for Structural Use in Internal Humid Conditions</i> (***) (EN 636 – 2 S)	EN 636 – 2 – S (***) (structural)	Load-bearing structural panels in dry covered service conditions (***) (EN 1995-1-1 - Service Class 1 or 2) for FLOORING or ROOFING.	2+

(*) Assessment and Verification of Constancy of Performance system according to Annex V of regulation (EU) No 305/2011

(**) Batch identification: 7-digit number on bundle

(***) Glue bond satisfies to the EN 636-3 class. However, the exterior conditions may correspond to the biological Hazard Class 3 to EN 335, for which this product cannot be used without further treatment or coating.

Notified Body Reference

Notified Body	Certificate or Assessment	Tasks performed for AVCP
Element Materials Technology Rotterdam B.V. Zekeringstraat 33 - 1014 BV Amsterdam - Netherlands	2812 – CPR – 0122 EC Certificate of factory Production Control from 24/11/2020	Initial inspection of factory Continuous Surveillance Certification of Factory Production Control

Declared Performance

The declared properties of the product are given in the table overleaf, based on the following Harmonised Technical Specifications:

EN 13986:2004+A1:2015 – Wood-based panels for use in construction – Characteristics, evaluation of conformity and marking

EN 636:2012+A1:2015 – Plywood - Specifications

Installation instructions and safety data sheets can be found on www.lumin.com.

The performance of the product identified is in conformity with the declared performance. This declaration of performance is issued under the sole responsibility of the manufacturer identified above.

For and on behalf of the manufacturer by:

09/12/2021 in Tacuarembó, Uruguay

Alvaro Molinari
Industrial Manager - Uruply S.A.

Thin peel 5.5 and 15 mm panels are not yet available as CE2+ Structural application panels

Essential Characteristics			Performance for indicated Panel Thickness (mm)				
			5.5	9	12	15	18
Panel Layout ¹⁾			EEE	EEEE	EEEE	EEEE	EEEEEE
Characteristic Strength ^{2) 3)}							
Bending – parallel	$f_{m,0,k}$	(N/mm ²)	NPD	30.0	30.0	NPD	20.0
Bending – perpendicular	$f_{m,90,k}$	(N/mm ²)	NPD	15.0	15.0	NPD	15.0
Compression	$f_{c,0,k}$	(N/mm ²)	NPD	NPD	NPD	NPD	NPD
Tension	$f_{t,0,k}$	(N/mm ²)	NPD	NPD	NPD	NPD	NPD
Panel Shear	$f_{v,k}$	(N/mm ²)	NPD	3.0	3.0	NPD	3.0
Planar Shear	$f_{r,k}$	(N/mm ²)	NPD	0.5	0.5	NPD	0.5
Mean Stiffness (MOE) ⁴⁾							
Bending – parallel	$E_{m,0}$	(N/mm ²)	NPD	6 000	6 000	NPD	6 000
Bending – perpendicular	$E_{m,90}$	(N/mm ²)	NPD	2 000	2 000	NPD	2 000
Compression	$E_{c,0}$	(N/mm ²)	NPD	NPD	NPD	NPD	NPD
Tension	$E_{t,0}$	(N/mm ²)	NPD	NPD	NPD	NPD	NPD
Panel Shear	G_v	(N/mm ²)	NPD	300	300	NPD	300
Planar Shear	G_r	(N/mm ²)	NPD	20	20	NPD	20
Density							
Characteristic Density ²⁾	ρ_k	(kg/m ³)	430	430	430	430	430
Mean Density ⁵⁾	ρ_{mean}	(kg/m ³)	520	520	520	520	520
Bonding quality / durability			Bonding Class 3				
Biological Durability			Hazard Class 2				
Reaction to fire class			D-s2, d0				
Release of formaldehyde class			E1				
Water vapour permeability							
Wet cup	μ		70	70	70	70	70
Dry cup			200	200	200	200	200
Airborne sound insulation							
	R		NPD	22.20	23.80	25.10	26.10
Sound absorption							
	α						
Frequency range 250Hz to 500 Hz			0.10	0.10	0.10	0.10	0.10
Frequency range 1000Hz to 2000 Hz			0.30	0.30	0.30	0.30	0.30
Thermal Conductivity							
	λ	(W/m.K)	0.13	0.13	0.13	0.13	0.13
Release (Content) of Pentachlorophenol (PCP)			< 5 ppm	< 5 ppm	< 5 ppm	< 5 ppm	< 5 ppm

1) P = Pine ; E = Eucalyptus

2) "Characteristic" = lower 5th percentile calculated as defined in EN 636:2012+A1:2015

3) The characteristic values are as specified in EN 12369-2:2004 and shall be modified for the given Service Class as described in EN 1995-1-1 using the relevant k_{mod} and k_{def} modification factors

4) The characteristic value for Stiffness should be taken as 0.8 times the mean value

5) The mean density for design should be taken as 1.1 times the characteristic value

Performance for Use in FLOORING or ROOFING Applications are declared in the table Overleaf

Thin peel 5.5 and 15 mm panels are not yet available as CE2+ Structural application panels

Essential Characteristics			Performance for indicated Panel Thickness (mm)				
			5.5	9	12	15	18
Panel Layup ¹⁾			EEE	EEEE	EEEE	EEEE	EEEEEE
Reaction to fire class for Flooring					D _{FL} -S1	D _{FL} -S1	D _{FL} -S1
Roofing – Cat. of Use H – spacing : 610 mm							
Characteristic Point Load	$F_{max,k}$	(kN)	NPD	NPD	2.50	NPD	4.04
Mean Stiffness	R_{mean}	(kN)	NPD	NPD	165	NPD	322
Serviceability Point Load	$F_{ser,k}$	(kN)	NPD	NPD	3.57	NPD	5.78
Soft Body Impact Resistance Class			NPD	NPD	I	NPD	I
Roofing – Cat. of Use H – spacing : 1220 mm							
Characteristic Point Load	$F_{max,k}$	(kN)	NPD	NPD	NPD	NPD	4.04
Mean Stiffness	R_{mean}	(kN)	NPD	NPD	NPD	NPD	99
Serviceability Point Load	$F_{ser,k}$	(kN)	NPD	NPD	NPD	NPD	5.78
Soft Body Impact Resistance Class			NPD	NPD	NPD	NPD	II
Flooring – Cat. of Use A – spacing : 500 mm							
Characteristic Point Load	$F_{max,k}$	(kN)	NPD	NPD	NPD	NPD	4.04
Mean Stiffness	R_{mean}	(kN)	NPD	NPD	NPD	NPD	496
Serviceability Point Load	$F_{ser,k}$	(kN)	NPD	NPD	NPD	NPD	5.78
Soft Body Impact Resistance Class			NPD	NPD	NPD	NPD	I
Flooring – Cat. of Use A – spacing : 610 mm							
Characteristic Point Load	$F_{max,k}$	(kN)	NPD	NPD	NPD	NPD	NPD
Mean Stiffness	R_{mean}	(kN)	NPD	NPD	NPD	NPD	NPD
Serviceability Point Load	$F_{ser,k}$	(kN)	NPD	NPD	NPD	NPD	NPD
Soft Body Impact Resistance Class			NPD	NPD	NPD	NPD	NPD
Racking Resistance for Walls			NPD	NPD	NPD	NPD	NPD
Soft Body Impact Resistance Class for Walls							
			NPD	NPD	NPD	NPD	NPD

1) P = Pine ; E = Eucalyptus

NOTE: Panels used for Flooring or Roofing application shall have their short edge supported by the joists and their long edge either tongued & grooved or entirely supported by and fixed to a noggings or batten.